

JORDAN ARMED FORCES  
SEPCIFICATIONS for GREEN COTTON TOWEL

1. Color shall be identical to the color of the appropriate standard pattern.
2. Yarn shall be evenly spun and of the type used in weaving towels fabrics.
3. Weft shall be extended from base yarn. Yarn shall take the shape of fuzzy circles not cut (terry) on both edges.
4. Yarn shall be evenly terry.
5. Edges shall be straight and firm.
6. Edges shall be folded and sewn firmly with a thread of the same color of fabric.
7. Towels shall be evenly woven from 100% cotton class A.
8. Towels shall be free of fuzz and falling fibers.
9. Color shall not fade out.
10. Dimensions (cm) length: 120, widths: 60 (Min).
11. Towel mass: 300 gm  $\pm$ 10 gm.
12. Filling material: free.
13. Change of dimension when washed: Length 4% , Width: 3 % (Max)
14. Absorption time: Eight seconds (Max).
15. Absorption: fabric shall absorb 6 times original weight (Min)
16. Color fastness to washing: change in color 4, Staining: 4-5 (Min)
17. Color fastness to perspiration: change in color 4, Staining: 4-5 (Min)
18. Tensile strength for warp: 215 N  $\pm$ 5 %
19. Tensile strength for weft: 280 N  $\pm$ 5 %
20. An increase in dimensions shall increase mass accordingly.
21. Quantity required (150000).

القوات المسلحة الاردنية  
مواصفات بشكير قطني لون أخضر زيتوني

1. اللون كلون العينه المتفق عليها ولا يقبل تفاوت باللون سوى المتعارف عليه.
2. الخيوط مغزوله بانتظام ومن النوع المستعمل لصناعة البشكير .
3. خيوط الطول والقاعدة على أساس حلقات زئبرية غير مقصوصه ( تيري) على جانبي البشكير .
4. الخيوط تري ومنتظمة.
5. الحاشية مستقيمه ومتينه.
6. حاشيتي الطول مثنية ومحاكة بشكل جيد ولون خيط الحياكة مثل لون البشكير .
7. القماش منسوجاً نسيجاً كاملاً من خيوط القطن (100% ) من النخب الممتاز.
8. القماش منسوجاً بانتظام وخالي من الرغب والعيوب وتساقط الألياف .
9. النزيف/ التلاشي اللوني غير مقبول .
10. الأبعاد ( سم ) : للطول : 120 للعرض 60 ( حد أدنى ) .
11. وزن البشكير : 300 غم ± 10 غم .
12. المواد المألنة: خالية.
13. تغير الأبعاد عند الغسيل: للطول 4% , للعرض 3% (حد أعلى).
14. زمن الأمتصاص : 8 ثواني (حد أعلى) .
15. الأمتصاص : يجب أن يمتص القماش 6 مرات ضعف وزنه الأصلي (حد أدنى).
16. ثبات اللون للغسيل: 4 تغير في اللون و 4-5 تبقيع ( حد أدنى ).
17. ثبات اللون للعرق: 4 تغير في اللون و 4-5 تبقيع ( حد أدنى ).
18. قوة الشد للطول: 215 نيوتن ±5% والزيادة مقبولة.
19. قوة الشد للعرض: 280 نيوتن ±5% والزيادة مقبولة.
20. الزيادة في الأبعاد يجب أن يتبعها زيادة في الوزن.
21. الكمية المطلوبة (150000) بشكير .